


Product	Monoseal WSP-175F		
Description	Monoseal WSP-175F is a single piece liner that provides a weld seal to PP containers. This liner will work with most applications including Food, Cosmetic and Pharma.		
Composition	Material	Metric	
	Polyester Film	0.0120 mm	
	Polyolefin Foam	0.1750 mm	
	Aluminium Foil	0.0250 mm	
	Polyester Film	0.0120 mm	
	Sealing Layer	0.0400 mm	
Overall	0.2640 mm		
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"		
GTR Oxygen	< 0.01 g/m2 .day	MVTR	<0.01cc/m2 .day
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.		

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

