


Product	Duoseal WEE-900P														
Description	Duoseal WEE-900P is a two piece wax bonded liner that provides a weld seal to PE/HDPE containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap														
Composition	<table border="1" style="width: 100%;"> <thead> <tr> <th style="text-align: left;">Material</th> <th style="text-align: left;">Metric</th> </tr> </thead> <tbody> <tr> <td>White lined Pulp</td> <td>0.9000 mm</td> </tr> <tr> <td>Wax Layer</td> <td>Specific to Application</td> </tr> <tr> <td>Aluminium Foil</td> <td>0.0250 mm</td> </tr> <tr> <td>Sealing Layer</td> <td>0.0500 mm</td> </tr> <tr> <td>Overall</td> <td>0.9750 mm</td> </tr> </tbody> </table>	Material	Metric	White lined Pulp	0.9000 mm	Wax Layer	Specific to Application	Aluminium Foil	0.0250 mm	Sealing Layer	0.0500 mm	Overall	0.9750 mm		
Material	Metric														
White lined Pulp	0.9000 mm														
Wax Layer	Specific to Application														
Aluminium Foil	0.0250 mm														
Sealing Layer	0.0500 mm														
Overall	0.9750 mm														
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"														
GTR Oxygen	< 0.01 g/m2 .day	MVTR	<0.01cc/m2 .day												
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.														

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

