






















Product	Duoseal WSE70-900PR																													
Description	Duoseal WSE70-900PR is a two piece wax bonded liner that provides a weld seal to PE/HDPE containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap																													
Composition	<table border="1"> <thead> <tr> <th style="text-align: left;">Material</th> <th style="text-align: left;">Metric</th> <th></th> </tr> </thead> <tbody> <tr> <td>White lined Pulp</td> <td>0.9000 mm</td> <td></td> </tr> <tr> <td>Polyester Barrier</td> <td>0.0120 mm</td> <td></td> </tr> <tr> <td>Wax Layer</td> <td>Specific to Application</td> <td></td> </tr> <tr> <td>Paper Layer</td> <td>65.0000 gsm</td> <td></td> </tr> <tr> <td>Aluminium Foil</td> <td>0.0250 mm</td> <td></td> </tr> <tr> <td>Polyester Barrier</td> <td>0.0120 mm</td> <td></td> </tr> <tr> <td>Sealing Layer</td> <td>0.0500 mm</td> <td></td> </tr> <tr> <td>Overall</td> <td>0.9990 mm</td> <td></td> </tr> </tbody> </table>	Material	Metric		White lined Pulp	0.9000 mm		Polyester Barrier	0.0120 mm		Wax Layer	Specific to Application		Paper Layer	65.0000 gsm		Aluminium Foil	0.0250 mm		Polyester Barrier	0.0120 mm		Sealing Layer	0.0500 mm		Overall	0.9990 mm			
Material	Metric																													
White lined Pulp	0.9000 mm																													
Polyester Barrier	0.0120 mm																													
Wax Layer	Specific to Application																													
Paper Layer	65.0000 gsm																													
Aluminium Foil	0.0250 mm																													
Polyester Barrier	0.0120 mm																													
Sealing Layer	0.0500 mm																													
Overall	0.9990 mm																													
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"																													
GTR Oxygen	< 0.01 g/m2 .day	MVTR	<0.01cc/m2 .day																											
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.																													

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC





Selpac Europe Ltd
Tishon House, Warrington Road
High Legh, Knutsford
Cheshire, WA16 0RT
Registered in England No: 6973836

Tel: +44 (0)1925 752600
Fax: +44 (0)1925 753395
Email: sales@selpac-europe.com
Web: www.selpac-europe.com
F20 Issue 1