






| | | | |
|--------------------------|--|-------------------------|--|
| Product | Duoseal WSP-900P | | |
| Description | Duoseal WSP-900P is a two piece wax bonded liner that provides a weld seal to PP containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap | | |
| Composition | Material | Metric | |
| | White lined Pulp | 0.9000 mm |  |
| | Wax Layer | Specific to Application |  |
| | Aluminium Foil | 0.0250 mm |  |
| | Polyester Barrier | 0.0120 mm |  |
| | Sealing Layer | 0.0400 mm |  |
| | Overall | 0.9770 mm | |
| FDA Status : | 21 CFR 177.1210 "Closures with sealing gaskets for food containers" | | |
| GTR Oxygen | < 0.01 g/m2 .day | MVTR | <0.01cc/m2 .day |
| Storage and Usage | The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office. | | |

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

