


Product	Duoseal N-PLP1-900P		
Description	DuosealN-PLP1-900P is a two piece waxless liner that provides a weld seal to PP containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap		
Composition	Material	Metric	
	White Pulp	0.9000 mm	
	Polyester Layer	0.0120 mm	
	Polyolefin	0.0250 mm	
	Aluminium Foil	0.0250 mm	
	Sealing Layer	0.0400 mm	
	Overall	1.0020 mm	
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"		
GTR Oxygen	< 0.01 g/m2 .day	MVTR	<0.01cc/m2 .day
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.		

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

