
















Product	Duo Peel PLSP-900P																							
Description	Duo Peel PLSP-900P is a two piece liner that provides a clean peel seal to PP containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap																							
Composition	<table border="1" style="width: 100%;"> <thead> <tr> <th style="text-align: left;">Material</th> <th style="text-align: left;">Metric</th> <th></th> </tr> </thead> <tbody> <tr> <td>White Pulp</td> <td>0.9000 mm</td> <td></td> </tr> <tr> <td>Wax Layer</td> <td>Application Specific</td> <td></td> </tr> <tr> <td>Aluminium Foil</td> <td>0.0250 mm</td> <td></td> </tr> <tr> <td>Polyester Barrier</td> <td>0.0120 mm</td> <td></td> </tr> <tr> <td>Sealing Layer</td> <td>0.0400 mm</td> <td></td> </tr> <tr> <td>Overall</td> <td>0.9770 mm</td> <td></td> </tr> </tbody> </table>	Material	Metric		White Pulp	0.9000 mm		Wax Layer	Application Specific		Aluminium Foil	0.0250 mm		Polyester Barrier	0.0120 mm		Sealing Layer	0.0400 mm		Overall	0.9770 mm			
Material	Metric																							
White Pulp	0.9000 mm																							
Wax Layer	Application Specific																							
Aluminium Foil	0.0250 mm																							
Polyester Barrier	0.0120 mm																							
Sealing Layer	0.0400 mm																							
Overall	0.9770 mm																							
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"																							
GTR Oxygen	< 0.01 g/m ² .day	MVTR	<0.01cc/m ² .day																					
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.																							

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

