


Product	Duoseal WEG-900P		
Description	Duoseal WEG-900P is a two piece wax bonded liner that provides a weld seal to Glass containers. This liner will separate leaving a foil seal across the neck and backing reseal board in the cap		
Composition	Material	Metric	
	White lined Pulp	0.9000 mm	
	Wax Layer	Specific to Application	
	Aluminium Foil	0.0250 mm	
	Sealing Layer	0.0500 mm	
Overall	0.9750 mm		
FDA Status :	21 CFR 177.1210 "Closures with sealing gaskets for food containers"		
GTR Oxygen	< 0.01 g/m ² .day	MVTR	<0.01cc/m ² .day
Storage and Usage	The ideal temperature for storage and transport is 15 - 30 Centigrade and 40 - 60% relative humidity without high pressure. Failure to store the goods at the recommended storage condition may lead to unexpected failure of the material and not covered by any implied or actual warranty. A full copy of the recommended storage and transport condition are available from the Selpac office.		

Selpac materials are compliant with limitations of heavy metals in packaging per CONEG & EU 94/62/EC

