



**Storage Recommendations and Shelf Life Guidelines for Selpac Lining Material**  
**(Document PS0002)**

**STORAGE RECOMMENDATIONS**

It is recommended that all Selpac products are stored at temperatures between 10-35°C and 40-60% Relative Humidity. However, for DuOSeal and DuOPeel it is recommended that they are stored between 10-30°C. Storage temperatures outside these limits increase the possibility of bowing, shrinking, curling, print transfer and for DuOSeal, premature absorption of the wax based adhesive.

If materials are overheated or chilled during transportation or storage, it is advisable to store them in the recommended temperature range, until equilibrated, before processing further.

**TIME STORAGE RECOMMENDATION**

It is recommended that lining materials are wadded, and lined caps used within the following times of our despatch/invoice date.

Product	Initial Wadding	Material in Caps
MonOSeal 1 pc	12 months	12 months
MonOPeel 1 pc	12 months	12 months
DuOSeal 2 pc	9 months	3 months
DuOPeel 2 pc	9 months	3 months
MonOLiner	12 months	12 months

**TESTING**

Before bulk orders are placed, we strongly recommend that liner/closure dimensions and closure design are discussed and checked with us.

The technical information contained herein is based on our tests and on information believed to be reliable, but we can assume no responsibility for the function of these materials in operation not under our direct control. No guarantee of the behaviour of these materials is either expressed or implied in this information sheet. We strongly recommend that laboratory tests are carried out to determine the suitability of the liner material being considered for any given application. This information does not preclude the necessity for you to check the suitability of our product for its intended use.

